Low Cement Alumina Castable 70% Al2O3 P-CAST-A70L

Castables & Ramming Mixes

Material type: Dense refractory concrete (Low Cement Castable)
Raw material basis: High alumina chamotte and bauxite and special additives

Al2O3	Bulk density	Grain size	Cold crushing strength (1…
69 – 71 %	2.45 – 2.55 g/cm³	0 – 8 mm	Min. 450 kg/cm²

Applications

- Industrial furnaces, burners and stacks with medium to high service temperatures
- Refractory repairs and linings in the steel, cement and petrochemical industries

Chemical analysis

Component	Value	Unit
Al_2O_3	69 – 71	%
MgO	Max. 0.8	%
CaO	1 – 2.5	%
Fe_2O_3	Max. 2	%
TiO_2	Max. 1.5	%

Physical properties

Property	Value	Unit
Bonding system	Hydraulic	
Grain size	0 – 8	mm
Maximum service temperature	1620	°C
Bulk density	2.45 – 2.55	g/cm³
Cold crushing strength (110 °C)	Min. 450	kg/cm²
Cold crushing strength (1100 °C)	Min. 400	kg/cm²

Packaging & storage

Packaging: 25 kg bags (dry mix, water is added on site)
Shelf life: 6 months (dry, cool, frost-free place)

Notes

Installation: casting with vibration; water addition and drying according to the manufacturer's instructions.

The values in this datasheet are typical results of laboratory tests on production samples and do not constitute a guaranteed specification. Consult the Pas Espadana technical team for your specific application.

Pas Espadana Refractory Co. (Private Joint Stock)
No. 12, 4th West Street, Sejzi Industrial Estate, Isfahan, Iran
Tel: 031-46413164 Email: info@pasnasooz.ir pasnasooz.ir