

Low Cement Alumina Castable 85% Al₂O₃, with Chromium Oxide P-CAST-A85Cr

Castables & Ramming Mixes

Material type: Low cement, dense refractory concrete (Low Cement Castable)

Raw material basis: Bauxite and special additives



Al₂O₃

82 – 85 %

Bulk density

2.5 – 2.9 g/cm³

Grain size

0 – 8 mm

Cold crushing strength (1...

450 – 550 kg/cm²

Applications

- Industrial furnaces, burners and stacks with medium to high service temperatures
- Refractory repairs and linings in the steel, cement and petrochemical industries

Chemical analysis

Component	Value	Unit
Al ₂ O ₃	82 – 85	%
MgO	Max. 0.5	%
CaO	1 – 2.5	%
Fe ₂ O ₃	Max. 2	%
TiO ₂	Max. 3	%
SiO ₂	Max. 8	%

Physical properties

Property	Value	Unit
Bonding system	Hydraulic	
Grain size	0 – 8	mm
Maximum service temperature	1700	°C
Bulk density	2.5 – 2.9	g/cm ³
Cold crushing strength (110 °C)	450 – 550	kg/cm ²

Packaging & storage

Packaging: 25 kg bags (dry mix, water is added on site)
Shelf life: 6 months (dry, cool, frost-free place)

Notes

Installation: casting with vibration; water addition and drying according to the manufacturer's instructions.

The values in this datasheet are typical results of laboratory tests on production samples and do not constitute a guaranteed specification. Consult the Pas Espadana technical team for your specific application.