

Alumina Castable 40% Al₂O₃, High Strength P-CAST-A40HS

Castables & Ramming Mixes

Material type: Dense refractory concrete (Conventional Castable)

Raw material basis: High alumina chamotte and special additives



Al₂O₃

Min. 40 %

Bulk density

Approx. 2.1 g/cm³

Grain size

0 – 5 mm

Cold crushing strength (...)

Min. 400 kg/cm²

Applications

- Linings of furnaces and thermal equipment up to 1300 °C
- General refractory linings and repairs

Chemical analysis

Component	Value	Unit
Al ₂ O ₃	Min. 40	%
CaO	8 – 10	%

Physical properties

Property	Value	Unit
Bonding system	Hydraulic	
Grain size	0 – 5	mm
Maximum service temperature	1300	°C
Bulk density	Approx. 2.1	g/cm ³
Cold crushing strength (110 °C)	Min. 400	kg/cm ²

Packaging & storage

Packaging: 40 kg bags (dry mix, water is added on site)

Shelf life: 6 months (dry, cool, frost-free place)

Notes

Installation: casting with vibration; water addition and drying according to the manufacturer's instructions.

The values in this datasheet are typical results of laboratory tests on production samples and do not constitute a guaranteed specification. Consult the Pas Espadana technical team for your specific application.