Alumina Castable 94% Al2O3 P-CAST-A94

Castables & Ramming Mixes

Material type: Dense refractory concrete (Conventional Castable)
Raw material basis: Tabular alumina and special additives

Al2O3	Bulk density	Grain size	Cold crushing strength (…
93 – 95 %	**2.8 – 3 g/cm³**	**0 – 5 mm**	**Min. 700 kg/cm²**

Applications

- High-temperature zones of furnaces in the steel, petrochemical and cement industries
- Precast shapes and refractory blocks for severe service

Chemical analysis

Component	Value	Unit
Al_2O_3	93 – 95	%
MgO	Max. 0.15	%
CaO	3 – 4.5	%
Fe_2O_3	Max. 0.5	%
TiO_2	Max. 0.15	%
SiO_2	Max. 0.5	%

Physical properties

Property	Value	Unit
Bonding system	Hydraulic	
Grain size	0 – 5	mm
Maximum service temperature	1800	°C
Bulk density	2.8 – 3	g/cm³
Cold crushing strength (110 °C)	Min. 700	kg/cm²
Cold crushing strength (1100 °C)	Min. 550	kg/cm²

Packaging & storage

Packaging: 25 kg bags (dry mix, water is added on site)
Shelf life: 6 months (dry, cool, frost-free place)

Notes

Installation: casting with vibration; water addition and drying according to the manufacturer's instructions.

The values in this datasheet are typical results of laboratory tests on production samples and do not constitute a guaranteed specification. Consult the Pas Espadana technical team for your specific application.

Pas Espadana Refractory Co. (Private Joint Stock)
No. 12, 4th West Street, Sejzi Industrial Estate, Isfahan, Iran
Tel: 031-46413164 Email: info@pasnasooz.ir pasnasooz.ir