

TECHNICAL DATA

P-CAST-A90L

Low Cement Castable

جرم ریختنی آلومینایی ۹۰% آلومینا - کم سیمان

Type of Material

Dense Refractory Concrete

Raw Material Basis

Bauxite and Tabular Alumina

Physical Properties

Bonding System	Granulation	Maximum Temp. of Application	Bulk Density
Hydraulic	0 - 8 mm	1750 'C	2.7 - 2.8 gr/Cm3

Temperature	C.C.S.
110 'C	500 - 580 Kg/Cm2
800 'C	----
1100 'C	420 - 500 Kg/Cm2

Chemical Analysis (%)

Al ₂ O ₃	MgO	CaO	Fe ₂ O ₃	TiO ₂	SiO ₂	SiC	Cr ₂ O ₃	ZrO ₂	Alkalies	C	L.O.I.
89 - 91	Max. 0.4	1 - 2.5	Max. 1.3	Max. 1.5	Max. 7	----	----	----	----	----	----

Condition as Delivered

25 Kg Bags, Dry for addition of water

Shelf Life

6 Months (dry, cool, frost free place)

Installation Method

Casting / Vibrating

All data listed are reference values subject to production related tolerances. Although reasonable care has been taken in the preparation of the information contained herein, it still remains the duty of the user to prove the suitability of this material for his applications.

